AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listing, of claims in the application:

LISTING OF CLAIMS:

1. (Currently Amended) A molding composition comprising:

I. at least two components selected from the group consisting of aromatic poly(ester) carbonates, graft polymers of one or more vinyl monomers on one or more graft bases having a glass transition temperature of < 10°C, a thermoplastic vinyl (co)polymer or poly(alkylene terephthalate), and

II. 0.5 to 25 parts by weight of a mixture of phosphorus compounds represented by the following formulas (I-a) and (I-b) ~~of the general formula (I)~~



(I),



(I-a)

and



(I-b)

wherein independently for each of formulas (I-a) and (I-b)

~~X denotes a mononuclear or polynuclear aromatic radical with 6 to 30 C atoms,~~

X^1 and X^2 are each independently represented by the following formula (II),



(II),

for which

A^1 denotes a member selected from the group consisting of C_1-C_5 alkylene, C_2-C_5 alkylidene, C_5-C_6 cycloalkylidene, -O-, -SO-, -CO-, -S-, $-SO_2$-, C_6-C_{12} arylene, each optionally condensed with further aromatic rings optionally containing heteroatoms, and a radical of the formula



(III)

or a radical of the formula (IV)



IV

and where

B independently of one another denotes C_1-C_8 alkyl, C_6-C_{10} aryl, C_7-C_{12} aralkyl,

x is in each case independently of one another 0, 1 or 2,

p is 1 or 0, and

R^6 and R^7 for each Z, independently of one another denote hydrogen or C_1-C_6 alkyl,

Z denotes carbon, and
m denotes an integer from 4 to Z,
with the proviso that on at least one atom Z, R^6 and R^7 are simultaneously alkyl

R^1, R^2, R^3 and R^4 independently of one another denote optionally halogenated C_1-C_8 alkyl or unsubstituted or substituted C_5-C_6 cycloalkyl, C_6-C_{20} aryl or C_7-C_{12} aralkyl where the substituents are selected from at least one of the group consisting of halogen and C_1-C_4-alkyl

n independently of one another denotes 0 or 1,

q denotes 0.5 to 30,

with the proviso that said mixture of phosphorous compounds contains at least ~~2~~ 1 phosphorus compounds ~~of the~~ represented by formula (I-a) and at least 1 phosphorous compound represented by formula (I-b), and the phosphorous compounds of formulas (I-a) and (I-b) ~~that~~ differ one from the other in at least one of their respective X^1, X^2, R^1, R^2, R^3 or R^4 groups, and wherein the sum of the parts by weight of the components is 100.

2. (Cancelled)

3. (Cancelled)

4. (Currently Amended) The composition of Claim 1 wherein ~~X is~~ X^1 and X^2 are each independently derived from a member selected from the group consisting of bisphenol A, resorcinol, hydroquinone~~, dihydroxydiphenyl~~ and dihydroxydiphenyl sulfone.

5. (Currently Amended) The composition of Claim 1 wherein the mixture of phosphorous compounds contains at least one phosphorus compound according to

formula (I-c),



(I-c),

in which Y denotes an isopropylidene radical, R^5 independently denotes C_1-C_4 alkyl or halogen, and k denotes 0, 1 or 2.

6. (Original) The composition according to Claim 1 wherein the graft copolymer is based on at least 2 monomers selected from the group consisting of chloroprene, butadiene-1,3, isoprene, styrene, acrylonitrile, ethylene, propylene, vinyl acetate and (meth)acrylic acid esters with 1 to 18 C atoms in the alcohol component.

7. (Currently Amended) The composition of Claim 6 wherein the graft polymer is based on:

B.1 5 to 95 parts by weight relative to 100 parts of the graft polymer of a mixture of

B.1.1 50 to 99 parts by weight relative to 100 parts of B.1 of at least one member selected from the group consisting of styrene, α-methylstyrene, halogen-nuclear-substituted and methyl-nuclear-substituted styrenes and methyl methacrylate, and

B.1.2 1 to 50 parts by weight relative to 100 parts of B.1 of at least one member selected from the group consisting of ~~selected from the group consisting of~~ acrylonitrile, methacrylonitrile, methylmethacrylate, maleic anhydride, C_1-C_4 alkyl-substituted maleimide and N-phenyl-substituted maleimide, and

B.2 5 to 95 parts by weight relative to 100 parts of B of polymer based on at least one member selected from the group consisting of diene and alkyl acrylate having a glass transition temperature of below -10°C.

8. (Original) The composition according to Claim 7, wherein B.2 is a member selected from the group consisting of polybutadiene, polyisoprene, butadiene/styrene copolymer, butadiene/acrylonitrile copolymer and acrylate rubber.

9. (Currently Amended) The composition according to Claims 1 wherein vinyl monomer is at least one member selected from the group consisting of vinyl aromatic compound, vinyl cyanide, (meth)acrylic acid-(C_1-C_8)-alkyl ester, unsaturated carboxylic acid, and a derivative of an unsaturated carboxylic acid.

10. (Currently Amended) The composition according to Claim 1 further ~~containing~~ comprising an anti-drip agent.

11. (Currently Amended) A molding composition comprising:

A) 5 to 95 parts by weight relative to 100 parts of the composition of at least one member selected from the group consisting of an aromatic polycarbonate and polyester carbonate,

B) 1 to 60 parts by weight relative to 100 parts of the composition of at least one graft polymer of

B.1 5 to 95 wt.% relative to the weight of B) of one or more vinyl monomers on

B.2 5 to 95 wt.% relative to the weight of B) of one or more graft bases having a glass transition temperature of < 10°C,

C) 0 to 50 parts by weight relative to 100 parts of the composition of a member selected from the group consisting of a thermoplastic vinyl (co)polymer and thermoplastic poly(alkylene terephthalate)

D) 0.5 to 25 parts by weight relative to 100 parts of the composition of a

mixture of phosphorus compounds ~~of the general formula (I)~~ represented by the following formulas (I-a) and (I-b) ~~of the general formula (I)~~



(I),



(I-a)

and



(I-b)

wherein independently for each of formulas (I-a) and (I-b),

~~X denotes a mononuclear or polynuclear aromatic radical with 6 to 30 C-atoms,~~

X^1 and X^2 are each independently represented by the following formula (II),



(II).

for which

A^1 denotes a member selected from the group consisting of C_1-C_5 alkylene, C_2-C_5 alkylidene, C_5-C_6 cycloalkylidene, -O-, -SO-, -CO-, -S-, $-SO_2$-, C_6-C_{12} arylene, each optionally condensed with further aromatic rings optionally containing heteroatoms, and a radical of the formula



(III)

or a radical of the formula (IV)



IV

and where

B independently of one another denotes C_1-C_8 alkyl, C_6-C_{10} aryl, C_7-C_{12} aralkyl,

x is in each case independently of one another 0, 1 or 2,

p is 1 or 0, and

R^6 and R^7 for each Z, independently of one another denote hydrogen or C_1-C_6 alkyl,

Z denotes carbon, and

m denotes an integer from 4 to 7,

with the proviso that on at least one atom Z, R^6 and R^7 are simultaneously alkyl

R^1, R^2, R^3 and R^4 independently of one another denote optionally halogenated C_1-C_8 alkyl or unsubstituted or substituted C_5-C_6 cycloalkyl, C_6-C_{20} aryl or C_7-C_{12} aralkyl where the substituents are selected from at least one of the group consisting of

halogen and C_1-C_4-alkyl

n independently of one another denotes 0 or 1,

q denotes 0.5 to 30, and

E) 0.05 to 5 parts by weight of anti-drip agent,

with the proviso that the mixture of phosphorous compounds ~~composition~~ contains at least ~~2~~ 1 phosphorus compounds ~~of the~~ represented by formula (I-a) and at least 1 phosphorous compound represented by formula (I-b), and the phosphorous compounds of formulas (I-a) and (I-b) differ one from the other in at least on of their respective ~~in which~~ X^1, X^2, ~~or one or more radicals~~ R^1, R^2, R^3 and R^4 groups ~~in one compound is different from the other~~, and

wherein the sum of the parts by weight is 100.

12. (Original) A method of using the composition of Claim 1 comprising producing a molded article.

13. (Original) A molded article comprising the composition of Claim 1.

14. (Added) The composition of Claim 11 comprising a first phosphorous compound represented by formula (I-a) and a second phosphorous compound represented by formula (I-b), wherein,

for said first phosphorous compound,

R^1, R^2, R^3 and R^4 are each phenyl,

n is 1,

q is 1.1, and

X^1 is represented by the following formula,



and

for said second phosphorous compound,

R^1, R^2, R^3 and R^4 are each phenyl,

n is 1,

q is 1, and

X^2 is represented by the following formula,



further wherein said composition has a weight ratio of said first phosphorous compound to said second phosphorous compound selected from 1.0 : 1.0, 3.6 : 1.0 and 0.40 : 1.0.

15. (Added) The composition of Claim 11 wherein said composition consists of components A) through E).